



TECHNICAL DATA SHEET

DECO-PP C0004T2 reprocessed

PROPERTIES		STANDARD	UNIT	TYPICAL VALUES
PHYSICAL & THERMAL				
Density		ISO 1183	g/cm ³	1,05
Ash Content	625°C	ISO 3451-1	%	20
Melt Flow Index		ISO 1133	g/10min	12
MECHANICAL				
Tensile Strength at Yield		ISO 527	MPa	25
Tensile Modulus		ISO 527	MPa	2000
Charpy - Notched Impact Strength	-20°C	ISO 179/1eU	KJ/m ²	18
Charpy - Notched Impact Strength	23°C	ISO 179/1eA	KJ/m ²	3,5
Charpy – Unnotched Impact Strength	-20°C	ISO 179/1eA	KJ/m ²	1,8

The information contained herein are supplied in good faith and given purely as an indication. Properties should be carefully evaluated for all projects requirements. Unless otherwise posted this product is not suitable for food and/or medical application and use. They shall not be considered in any way as a formal commitment or warranty on our part especially in case of improper use of our products from third parties.

24.07.2017