



## TECHNICAL DATA SHEET

# DECOLan G3 black (ABS GF15)

PROPERTIES		STANDARD	UNIT	TYPICAL VALUES
<b>PHYSICAL &amp; THERMAL</b>				
MVR	220°/10kg	ISO 1133	cm <sup>3</sup> /10min	3-5
Ash Content	750°C/60min	ISO 3451-1	%	15-17

*The information contained herein are supplied in good faith and given purely as an indication. Properties should be carefully evaluated for all projects requirements. Unless otherwise posted this product is not suitable for food and/or medical application and use. They shall not be considered in any way as a formal commitment or warranty on our part especially in case of improper use of our products from third parties.*

21.02.2019